

PFINDER 800

COLOR CONTRAST PENETRANT

RED + FLUORESCENT

Type II+III | Sensitivity Level 2



Version 19 | 28.02.2023 | Page 1/1

DESCRIPTION

PFINDER 800 is a hydrocarbon-free, directly water-washable fluorescent penetrant for crack detection of surfaces. PFINDER 800 is readily biodegradable according to ISO 9888 / Zahn-Wellens-EMPA test (OECD 302 B). Details and test report available on request.

Due to its removability PFINDER 800 provides only a low residual background even on rough surfaces and therefore a user-friendly interpretability of the indications.

PFINDER 800 is qualified for penetrant testing at temperatures between $-20\text{ }^{\circ}\text{C}$ to $+100\text{ }^{\circ}\text{C}$ (temperature of work part) according to EN ISO 3452-5 and EN ISO 3452-6.

Penetrant type II+III according DIN EN ISO 3452-1.
Use: Type II+III, Method A+C, Form a, b, c, e, f

APPLICATION

The capability of the penetrant system should be checked regularly by means of own reference pieces or e.g. reference test block 2 according EN ISO 3452-3. Process description according DIN EN ISO 3452-1 see www.pfinder.com.

For applications at temperatures below $+10\text{ }^{\circ}\text{C}$ and above $+50\text{ }^{\circ}\text{C}$, penetration time has to be adapted as follows:

- + $100\text{ }^{\circ}\text{C}$ to $+50\text{ }^{\circ}\text{C}$: penetration time up to 15 minutes
- + $50\text{ }^{\circ}\text{C}$ to $+10\text{ }^{\circ}\text{C}$: according DIN EN ISO 3452-1 and EN ISO 3452-2
- + $10\text{ }^{\circ}\text{C}$ to $0\text{ }^{\circ}\text{C}$: usual penetration time x 2
- $0\text{ }^{\circ}\text{C}$ to $-10\text{ }^{\circ}\text{C}$: usual penetration time x 3
- $10\text{ }^{\circ}\text{C}$ to $-20\text{ }^{\circ}\text{C}$: usual penetration time x 4

Values are referring to the temperature of the working part. Aerosol spray cans must not be warmed up above $+50\text{ }^{\circ}\text{C}$.



YOUR GREEN NDT BENEFITS

- | Readily biodegradable - no waste water treatment required
- | Free of aromatics and azo compounds
- | Aerosol spray can with minimized carbon footprint



YOUR HANDLING + COST SAVING BENEFITS

- | Bright, sharp indications with high contrast
- | Easy rinsability = low background fluorescence
- | Reduced consumption due to low viscosity

APPROVALS & CONFORMITIES

The product conforms to these specifications / is suitable for the use according to:

EN ISO 3452-2 | 3452-5 | 3452-6 |
VDA236-150 | ASTM E165 |
ASTM E1417 | ASME V Art.6

Low content of sulfur and halogens according to EN ISO 3452-2.

PACKAGING

500-ml-spray can (for 360° application) | 5-l-canister | 200-l-drum
These packages are on stock and instantly available. Other packages on demand.

SHELF-LIFE & STORAGE

3 years
Storage between $+5\text{ }^{\circ}\text{C}$ and $+45\text{ }^{\circ}\text{C}$.
Shake or stir well before use!

CHARACTERISTIC DATA	Specification	Unit	Value
Density/ $20\text{ }^{\circ}\text{C}^*$	DIN 51 757	kg/m ³	970 \pm 48
Viscosity/ $20\text{ }^{\circ}\text{C}^*$	ASTM D 7042	mm ² /s	approx. 15,5
Flash Point*	EN ISO 2719	$^{\circ}\text{C}$	> 105
Productivity	500 ml Aerosol spray can	m ²	up to 10

* Data of products packaged in aerosol spray cans might differ.